

THOMSON

DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

[Home](#) | [Web Files](#) | [Publications](#) | [My Account](#) | [Products](#)
Search: [Quick/Number](#) [Boolean](#) [Advanced](#) [Derwent](#)

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: [Create new Work File](#)View: [INPADOC](#) | Jump to: [Top](#) Go to: [Derwent](#)[Email this to a](#)Title: **JP57138774A2: BATTERY**Derwent Title: Organic electrolyte battery with no liquid leakage - has sealing layer consisting of solid paraffin and photohardening resin ([Derwent Record](#))

Country: JP Japan

Kind: A

Inventor: EDA NOBUO;
TOYOGUCHI YOSHINORI;
YOSHIMOTO KEIKO;
MORITA TERUYOSHI;Assignee: MATSUSHITA ELECTRIC IND CO LTD
[News, Profiles, Stocks and More about this company](#)

Published / Filed: 1982-08-27 / 1981-02-19

Application Number: JP1981000024095

IPC Code: H01M 2/08; H01M 6/16;

Priority Number: 1981-02-19 JP1981000024095


Abstract: PURPOSE: To improve the preserving property of a battery, by forming a sealing layer with a solid paraffin layer and a photosetting resin layer provided outside, in a battery where a resin-sealing layer is used to hermetically seal a negative electrode made of light metal.

CONSTITUTION: In a battery case 1, there are a positive electrode 2 made of graphite fluoride etc, a separator 3 and a liquid-holding material 4 mainly impregnated with an organic electrolytic solution. In the same battery case 1, there is an insulated cylinder 7 which contains a lithium negative electrode 5 and a collector 6 thereof. The battery case 1 is hermetically sealed with an epoxide resin layer 11 to form an organic electrolyte battery. In this case, a sealing layer is composed of a solid paraffin layer 9 inside, further a photosetting resin layer 10 outside, and said epoxide resin layer 11. The photosetting resin layer 10 made of denatured acrylate resin is poured onto the paraffin layer 9, and then forced to set by irradiation of ultraviolet-rays.

COPYRIGHT: (C)1982,JPO&Japio

Family: None

Other Abstract Info: CHEMABS 097(26)225613E



Best Available Copy



[Nominate](#)



[this for the Gallery...](#)

© 1997-2004 Thomson

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **57138'**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **56024095**(51) Intl. Cl.: **H01M 2/08**(22) Application date: **19.02.81**

<p>(30) Priority:</p> <p>(43) Date of application publication: 27.08.82</p> <p>(84) Designated contracting states:</p>	<p>(71) Applicant: MATSUSHITA ELECTRIC INC. LTD</p> <p>(72) Inventor: EDA NOBUO TOYOGUCHI YOSHINORI YOSHIMOTO KEIKO MORITA TERUYOSHI</p> <p>(74) Representative:</p>
---	--

(54) BATTERY**(57) Abstract:**

PURPOSE: To improve the preserving property of a battery, by forming a sealing layer with a solid paraffin layer and a photosetting resin layer provided outside, in a battery where a resin-sealing layer is used to hermetically seal a negative electrode made of light metal.

CONSTITUTION: In a battery case 1, there are a positive electrode 2 made of graphite fluoride etc, a separator 3 and a liquid-holding material 4 mainly impregnated with an organic electrolytic solution. In the same battery case 1, there is an insulated cylinder 7 which contains a lithium negative electrode 5 and a collector 6 thereof. The battery case 1 is hermetically sealed with an epoxide resin layer 11 to form an organic electrolyte battery. In this case, a sealing layer is composed of a solid paraffin layer 9 inside, further a

photosetting resin layer 10 outside, and said epoxide resin layer 11. The photosetting resin layer 10 made of denatured acrylate resin is poured onto the paraffin layer 9, and then forced to set by irradiation of ultraviolet-rays.

COPYRIGHT: (C)1982,JPO&Japio

